

CK1

CRACKOLAC Crackle Finish

Page 1 of 1

FEATURES

- Fast drying, solvent-based coating
- Easily re-coatable with all top coats

USES

Interior furniture & joinery.

TOPCOAT

CK1-6-AA000-005	CRACKOLAC Crackle Top Coat Promatch
CK1-6-AA0ME-005	CRACKOLAC Crackle Top Coat Metallic
CK1-6-AS000-005	CRACKOLAC Crackle Top Coat SPECIAL

BASECOAT

CK1-7-AA000-005	CRACKOLAC Basecoat Promatch
-----------------	-----------------------------

BASECOAT PRIMER (OPTIONAL)

PC2-7-10320-005	PC2 MDF Primer (Melamine) WHITE
-----------------	---------------------------------

THINNERS (BASECOATS ONLY)

CL2-9-TH031-005	No 31 Anti Bloom Retarding Thinners
-----------------	-------------------------------------

CLEANER FOR EQUIPMENT

CL2-9-TH020-005	ISF Spray Gun & Brush Cleaner
-----------------	-------------------------------

APPLICATION EQUIPMENT

Conventional airless / airmix or HVLP spray equipment.

APPLICATION

Apply a good coat of PC2 MDF Primer onto RAW substrate and Prep as normal. Then apply a full wet coat of the CRACKOLAC Basecoat Promatch and allow to dry. light denib with 320 grit paper. CRACKOLAC CRACKLE Top Coat is supplied to be used straight from the can. The film thickness of the cracklecoat will determine the width of the cracks. A heavy coat will produce a wide crackle effect, a light coat will produce a finer effect. Once the crackle finish is dry - approx 2hr, it requires a clear lacquer to seal it in.

FURTHER INFORMATION

May be overcoated with all waterbased and solvent based type lacquers.



Coverage	Touch Dry	Recoat Time	Max Resistance	Pot Life	Mix Ratio	Shelf Life	Pack Size
8-10 Sq.m/ltr	5-10 mins	2 hrs	7 Days	N/A	N/A	12 months	1, 5 & 25lt

