

12760 Waterborne Supremacy Clear system

Page 1 of 1

FEATURES	<ul style="list-style-type: none"> • High quality Water based formulation • Fast cure times with excellent flow out & re-coat properties • Ultra-Clear transparency with good grain definition • FIRA 6250 Severe Use tested and approved
USES	Interior joinery & furniture.
TOPCOAT	12760 WB Supremacy Clear Dead Matt 12760 WB Supremacy Clear 10% 12760 WB Supremacy Clear 25% 12760 WB Supremacy Clear 50% 12760 WB Supremacy Clear 90%
BASECOAT	12759 WB Supremacy Clear Sanding Sealer (Optional)
THINNER FOR SYSTEM	12763 WB Supremacy thinners
CLEANER FOR EQUIPMENT	Water
APPLICATION EQUIPMENT	Conventional airless / airmix or HVLP spray equipment / Curtain coater
APPLICATION	Thin (if required) with the recommended 12763 WB Supremacy thinners by up to a maximum of 10% by volume, Water can be used but do not exceed 5% by volume. Apply an even coat (75-100 microns WFT) of 12759 WB Supremacy Sealer , allow to dry & de-nib with 240/320 grit. Then apply a full even wet coat of 12760 WB Supremacy Clear Topcoat (100-125 microns WFT) & allow to dry. Alternatively apply the Topcoat lacquer as a coat on coat system.
FURTHER INFORMATION	Please ensure that the total system film thickness (DFT) does not exceed 150 microns. Always lightly sand between coats to assist adhesion.

Coverage	Touch Dry	Recoat Time	Max Resistance	Pot Life	Mix Ratio	Shelf Life	Pack Size
4							
10-12 Sqm/Lt	20 mins	60 mins	7 Days	N/A	N/A	12 months	5lt & 20lt

