

SE1

Stoving Enamels

Page 1 of 1

FEATURES

- High quality resin blend - Heat resistance up to 250c
- Excellent gloss, flow, film clarity & colour retention
- Covers in ONE coat - no primer required
- Hardwearing, marr resistant. Contains anti-scuff additives

USES

Interior & Exterior metal work.

TOPCOAT

SE1-6-AA000-005	Stoving Enamel Promatch
SE1-6-AS000-005	Stoving Enamel Promatch SPECIAL
SE1-6-BL010-005	Stoving Enamel Black 10% Matt
SE1-6-BL025-005	Stoving Enamel Black 25% Eggshell
SE1-6-BL050-005	Stoving Enamel Black 50% Semi Gloss
SE1-6-BL090-005	Stoving Enamel Black 90% Gloss
SE1-6-WH010-005	Stoving Enamel White 10% Matt
SE1-6-WH025-005	Stoving Enamel White 25% Eggshell
SE1-6-WH050-005	Stoving Enamel White 50% Semi Gloss
SE1-6-WH090-005	Stoving Enamel White 90% Gloss

THINNER FOR SYSTEM

SET-9-TH158-005 No 158 Stoving Thinners

CLEANER FOR EQUIPMENT

CL2-9-TH020-005 ISF Spray Gun & Brush Cleaner

APPLICATION EQUIPMENT

Conventional airless / airmix or HVLP spray equipment.

APPLICATION

Clean surface with No 40 Dgreaser. Non ferrous metals should be primed with TP2 Epoxy primer. No 158 THINNERS or No 100 SUPERFLOW THINNERS may be added up to 10% by volume. Stoving schedule is 120c for 15 mins after 10 min flash off at room temperature.

FURTHER INFORMATION

Also available in a HAMMER FINISH version.

Please note: This product can also be supplied in 400 ml Aerosols with professional adjustable fan nozzels.



Coverage	Touch Dry	Recoat Time	Max Resistance	Pot Life	Mix Ratio	Shelf Life	Pack Size
8-10 Sq.m/lit	10-15 mins	90mins	7 Days	N/A	N/A	12 months	1, 5 & 25lt

