

PVO

PVC (Spray) System

FEATURES

- Ready for use formulation - no thinners/primer required
- Outstanding adhesion to PVC & Foamex
- Fast drying for speedy production schedules
- Easily re-coatable

USES

Coating for rigid & flexible PVC

TOPCOAT

PVO-6-AA000-005	PVC (Spray) Promatch
PVO-6-AS000-005	PVC (Spray) SPECIAL Promatch
PVO-6-BL010-005	PVC (Spray) Black 10% Sheen
PVO-6-BL025-005	PVC (Spray) Black 25% Sheen
PVO-6-BL050-005	PVC (Spray) Black 50% Sheen
PVO-6-BL090-005	PVC (Spray) Black 90% Sheen
PVO-6-WH010-005	PVC (Spray) White 10% Sheen
PVO-6-WH025-005	PVC (Spray) White 25% Sheen
PVO-6-WH050-005	PVC (Spray) White 50% Sheen
PVO-6-WH090-005	PVC (Spray) White 90% Sheen
PVO-6-AA0ME-005	PVC (Spray) Promatch Metallic
PVO-3-CL000-005	PVC (Spray) Clear

THINNER FOR SYSTEM

PVT-9-TH000-005 PVC Standard Thinners

CLEANER FOR SUBSTRATE

CL2-9-00077-005 No 77 PVC Degreaser (Strong)

CLEANER FOR EQUIPMENT

CL2-9-TH020-005 ISF Spray Gun & Brush Cleaner

APPLICATION EQUIPMENT

Conventional airless / airmix or HVLP spray equipment.

APPLICATION

Degrease substrate with No77 DEGREASER (STRONG) - Please note: No77 DEGREASER (STRONG) should not be used as a vigorous cleaner as it may soften and attack the PVC substrate, suggest a test application before use. Thinners not normally required, viscosity of this product is very low as it relies on the solvents in the formulation to both adhere & assist flexibility of the substrate.

FURTHER INFORMATION

Direct application - No Primer required.

Please note: This product can also be supplied in 400 ml Aerosols with professional adjustable fan nozzels.



Coverage

Touch Dry

Recoat
Time

Max
Resistance

Pot Life

Mix Ratio

Shelf Life

Pack Size

8-10 Sq.m/ltr

5 mins

60 mins

7 Days

N/A

N/A

12 months

1, 5 & 25lt

152/16

