

ST3C

Steri-Guard SG3 PU - CLEAR

Page 1 of 1

FEATURES

- Non biocide "safe to use" highly resistant hygienic coating
- Surpasses BS6250 Severe Use - Stain & Chip resistant
- Good flow & film clarity produces a superbly smooth finish
- Hardwearing with good mar & water resistance

USES

High quality interior joinery & furniture.

TOPCOAT

SG3-3-CL010-005	Steri-Guard SG3 - PU Clear 10% Sheen
SG3-3-CL025-005	Steri-Guard SG3 - PU Clear 25% Sheen
SG3-3-CL050-005	Steri-Guard SG3 - PU Clear 50% Sheen
SG3-3-CL090-005	Steri-Guard SG3 - PU Clear 90% Sheen

TOPCOAT CATALYST

RP1-8-NO.03-001	RP1 No.3 Cat for Clears (1lt)
-----------------	-------------------------------

BASECOAT

SG3-4-SE010-005	Steri-Guard SG3 - PU Clear Sealer
-----------------	-----------------------------------

BASECOAT CATALYST

RP1-8-NO.03-001	RP1 No.3 Cat for Clears (1lt)
-----------------	-------------------------------

THINNER FOR SYSTEM

RPT-9-TH000-005	RPT (PU) System Thinners
-----------------	--------------------------

CLEANER FOR EQUIPMENT

CL2-9-TH020-005	ISF Spray Gun & Brush Cleaner
-----------------	-------------------------------

APPLICATION EQUIPMENT

Conventional airless / airmix or HVLP spray equipment.

APPLICATION

MIX RATIO - Mix 4 Parts Steri-Guard PU Part A with 1 Part PU Catalyst. Apply a light coat of Steri-Guard PU Sanding Sealer, allow to dry, de-nib & apply another sealer coat as necessary. Then after a further de-nib apply a full even coat of the Steri-Guard PU Top Coat. Once catalysed, thinners not normally necessary, however RPT thinners may be used if required up to a maximum of 10% by volume. Allow to dry overnight prior to packing. Steri-Guard PU Lacquer may be used Coat on Coat. Do not use over pre-catalysed basecoats.

FURTHER INFORMATION

As the catalyst contains isocyanate the use of air-fed masks is required whilst spraying. ensure that the total system dry film thickness (DFT) exceed 150 microns. Always lightly sand between coats to assist adhesion. Maximum 2 coats in any 8 hours. Catalyst should be used within 6 weeks of delivery. Once opened the catalyst MUST be used within 7 days.



Coverage	Touch Dry	Recoat Time	Max Resistance	Pot Life	Mix Ratio	Shelf Life	Pack Size
8-10 Sq.m/ltr	15-20 mins	60 mins	7 Days	8 Hours	4:1	12 months	5 & 25lt

152/16

