

SG5

Steri-Guard TP5 Acrylic Epoxy - Non Isocyanate

Page 1 of 1

FEATURES

- Epoxy cured, acrylic resin that is free from isocyanates
- Excellent gloss and colour retention
- Offers high resistance to both weather and chemicals
- Non biocide "safe to use" highly resistant hygienic coating

USES

Interior & exterior metal work & plastics.

TOPCOAT

TP5-6-AA000-005	TP5 (Acrylic Epoxy) Promatch
TP5-6-AA00E-005	TP5 (Acrylic Epoxy) Promatch Metallic
TP5-6-AS000-005	TP5 (Acrylic Epoxy) Promatch SPECIAL
TP5-6-BL010-005	TP5 (Acrylic Epoxy) Black Top Coat
TP5-6-WH010-005	TP5 (Acrylic Epoxy) White Top Coat

TOPCOAT CATALYST

TP5-8-NO.01-005	TP5 Catalyst 19237 (5lt)
-----------------	--------------------------

BASECOAT

TP2-7-19888-005	19888 Epoxy Etch Primer Yellow Wash Zinc
TP2-7-GR010-025	TP2 Epoxy Primer GREY
TP2-7-RO010-025	TP2 Epoxy Primer RED OXIDE
TP2-7-WH010-025	TP2 Epoxy Primer WHITE

BASECOAT CATALYST

TP2-8-NO.01-005	TP2 Catalyst (5lt)
-----------------	--------------------

THINNER FOR SYSTEM

TPT-9-TH150-005	No 150 Two Pack Thinners
-----------------	--------------------------

CLEANER FOR SUBSTRATE

CL2-9-TH040-005	No 40 Solvent Degreaser
-----------------	-------------------------

CLEANER FOR EQUIPMENT

CL2-9-TH020-005	ISF Spray Gun & Brush Cleaner
-----------------	-------------------------------

APPLICATION EQUIPMENT

APPLICATION

Conventional airless / airmix or HVLP spray equipment.

FURTHER INFORMATION

Clean surfaces with No 40 Degreaser. Mix 4 parts A with 1 part B. Stir thoroughly. Prime as necessary dependant on substrate. Always sand lightly between coats to assist adhesion.

For exterior use: please ensure that the total system film thickness (DFT) exceeds 150 microns (3 coats). Always sand between coats to assist adhesion.



Coverage

Touch Dry

Recoat
Time

Max
Resistance

Pot Life

Mix Ratio

Shelf Life

Pack Size

8-10 Sq.m/lit

15-20 mins

Overnight

7 Days

24 hours

4:1

12 months

1, 5 & 25lt

