



the perfect finish
SINCE 1898

MANUFACTURING INNOVATIVE
SOLUTIONS FOR OVER 125 YEARS

ISF TECHNICAL DATA SHEET

NYLOFIX Adhesion Promoter



FEATURES

- Used extensively in the plastics & adhesives industry
- Easy application

USES	Advanced adhesion promoter for Nylon substrates
-------------	---

TOPCOAT	PVC (Spray) Promatch ACRYLAC F197 Styrene Promatch
----------------	---

CLEANER FOR SUBSTRATE	No 40 Solvent Degreaser
------------------------------	-------------------------

CLEANER FOR EQUIPMENT	ISF Spray Gun & Brush Cleaner
------------------------------	-------------------------------

APPLICATION EQUIPMENT	By Brush or Dipping
------------------------------	---------------------

APPLICATION PROCESS

Stir & mix the product well prior to use, supplied as 'ready for use' viscosity for hand application.

- Clean substrate with No 40 Solvent Degreaser
- Apply NYLOFIX by Dip or Brush and allow to dry
- Touch dry: 10 mins
- Only when fully dry (approx. 60 mins) may it then be overcoated with the recommended ISF topcoat
- Coverage: 15-20sqm

FURTHER INFORMATION

This product can also be supplied in 400 ml Aerosols with professional adjustable fan nozzles.
Storage Temperatures should be maintained above 5°C.



NYLOFIX Adhesion Promoter | Page 1 of 1

This version: March 2025

